



RECOMMENDED FABRICS

Nylon
100% Cotton
Some 50/50 Cotton/Polyester Blends
Nonwoven Polypropylene Bags (NPB)




INK APPLICATION

All-Pro™ 900 Series Ink must be mixed with the All-Pro™ 900 Catalyst before printing, for adhesion to Nylon substrates. For NPB, catalyst is not necessary



ADDITIVES

If modification is necessary, use 1% to 5% by weight of 1110 Curable Reducer. For NPB, 3804 Low Cure Additive can be added up to 6% by weight to lower cure temperature



SCREEN MESH

86-305 t/in (34-120 t/cm)
monofilament



EMULSION

Any direct or indirect emulsion or capillary film in the 35 to 70 micron range



SQUEEGEE

70-80 Durometer
Sharp edge



CURE TEMPERATURES

275°F to 325°F (135°C) to 163°C entire ink film. Fusing at lower temperatures may require a longer dryer retention time. +Metallic colors need longer dwell time.



CLEAN-UP

Any Eco-friendly plastisol screen wash



PRODUCT PACKAGING

Quart, 1 gallon, 5 gallon, 30 gallon or 50 gallon containers



STORAGE OF INK CONTAINERS

65°F to 90°F (18°C to 32°C)
Avoid storage in direct sunlight
Keep containers well sealed



SDS

Refer to SDS prior to use

FEATURES

All-Pro™ 900 Series Plastisol Ink is a fast flashing, 2 part ink, specifically formulated for printing on normally hard to print Nylon.

Being the industry standard for over 15 years, the ink's harder finish resists scratching, scuffing and peeling for an extremely durable image.

It can also be used without catalyst on nonwoven polyporpylene bags (NPB) by adding up to 6% 3804 Low Cure Additive, which reduces cure temperatures down to 250°F (135°C).

COLORS AVAILABLE

900 Catalyst **	908 Metallic Silver ⁺	917 Maroon
901 White	909 Metallic Gold ⁺	920 Clear
902 Black	911 Purple	926 Athletic Gold
903 Golden Yellow	912 Brown	931 Fluorescent Pink
904 Scarlet	913 Lemon Yellow	932 Fluorescent Yellow
905 Navy Blue	914 Process Cyan	937 Athletic Dark Orange
906 Royal Blue	915 Process Magenta	938 Fluorescent Green
907 Kelly Green	916 Process Yellow	939 Fluorescent Blue
		966 Athletic Light Royal

** Catalyst must be ordered separately

+ Metallic colors require longer cure dwell times due to the reflective nature of the metallic flakes.

INK APPLICATION

The All-Pro™ 900 Series Ink must be mixed with the All-Pro™ 900 Catalyst before printing on Nylon. Catalyst is available in 2 ounce, 8 ounce, and 1 gallon containers. The catalyst should be thoroughly mixed in to the ink to the following proportions:

By volume = 16 parts ink to 1 part catalyst
By weight = 20 parts ink to 1 part catalyst

1 ounce of catalyst to 1 pint of ink
2 ounces of catalyst to 1 quart of ink
8 ounces of catalyst to 1 gallon of ink

Ink may be used immediately after mixing. Do not mix more ink than is needed for a job. Do not under-catalyze the ink. Pot life of mixed ink is 4 to 8 hours. Over-catalyzation will shorten the pot life.

If printing on cotton, it is not necessary to catalyze the ink. Print it as you would a normal direct print plastisol ink.

For standard colors, recommended screen mesh is 125-230 t/in (49-90 t/cm). For metallic colors, recommended screen mesh is 86-110 t/in (34-43 t/cm). For process colors, recommended screen mesh is 200-305 t/in (79-120 t/cm).

IMPORTANT INFORMATION

Adding too much reducer or other additives to the 900 Series inks may cause curing/fusing or increased dye migration problems. Test dryer temperatures and wash test printed product before and during a production run.

DISCLAIMER

Recommendations and statements made are based on International Coatings' research and experience. Since International Coatings does not have any control over the conditions of use or storage of the product sold, International Coatings cannot guarantee the results obtained through use of its products. All products are sold and samples given without any representation of warranty, expressed or implied, of fitness for any particular purpose or otherwise, and upon condition that the buyer shall determine the suitability of the product for its own purpose. This applies also where rights of third parties are involved. It does not release the user from the obligation to test the suitability of the product for the intended purpose and application.